

Leaching Manhole

- General 4' diameter Manhole spec. can be used for Sewer, Drain Manholes & Catch Basins 1.
- 2. Concrete strength f'c 4000PSI@28 days. Density 150 PCF.
 - 3. Cement, Portland Type II or III, ASTM C150-18.
 - Reinforced Steel conforms to latest ASTM A1064 Spec. 0.12 SQ. IN./Lineal FT. and 0.12 SQ IN. 4. (Both ways) Base Bottom.
 - 5. Admixtures, air & plasticizers per ASTM C1116, C494, C260 and C1017.
 - 6. H20 & HL-93 Design Loading AASHTO HS-20-44; ASTM C478 specs for precast reinforced concrete manhole sections.
 - 7. Butyl resin joint seal conforms to latest ASTM C913, C990 & C443 specs.
 - Optional steel reinforced plastic steps meet ASTM A615 MA Industries type PS-2-PR-SL. 8.
 - 9. Holes cored to your plans/specifications. Drawings or plans must be submitted prior to any coring.
 - 10. Sewer Manholes are spray coated w/Agua Safe Waterproofer

87 Adams Hill Road, PO Box #333 Greenville, NH 03048 603-878-1340