



William N. Lamarre Concrete Products, Inc.

OPEN BOTTOM BOX CULVERT

Sizes Vary to meet specifications needed.

Drawing Not to Scale



Notes

1. Concrete strength f'c 5000PSI@28 days. Density 150 PCF.
2. Cement, Portland Type II or III, ASTM C150-81
3. Admixtures, air & plasticizers per ASTM C233-82
4. Design Loading AASHTO HS20-40
5. Constructions joints sealed with butyl rubber